



 $pratta.xyz \cdot or sochem.com \cdot pratta.xyz \cdot o$

ANTICO VELLUTO

Interior decorative plaster with the effect of Florentine silk



Main Characteristics

Description:



ANTICO VELLUTO is eco-friendly decorative coating with the effect of Florentine velvet fabric. The composition of the material includes natural pearl pigment and silk microadditives, providing not only high quality and great appearance, but also resistance to UV exposure.

Basic types of materials:

Cool – silver base, tinted in cold colors and shades Warm – light gold, tinted in warm colors and shades Gold – gold base, tinted in golden colors and shades

Usage:

The material is intended for finishing walls and ceilings in interiors, restoration of old and finishing of new buildings, as well as for finishing hotels, shopping and office centers or other public spaces. And also for finishing furniture elements and stucco decoration, etc.

Preparation

Use in interiors:





Before applying the ANTICO VELLUTO material, it is necessary to prepare the surface using the ORSO Infinity Basic and/or ORSO Infinity Light preparatory putty system. Surface preparation must comply with the building regulations for the preparation of walls in the interior for painting or international standards of category Q4 (K4).



The prepared surface should be smooth and even, without scratches and chips!

Apply 1-2 coats of fixative of a deep penetration PRIMER NORMAL diluted with water in a ratio of 1:8. The time of interlayer drying is 2 hours. Complete drying 4–6 hours (before use, we recommend that you read the technical description of the product).

Apply 1 layer of a special PRIMER LISCIO substrate (before use, we recommend that you read the technical description of the product). After applying the substrate, wait for it to dry completely: 6–8 hours. The substrate gives the surface the necessary adhesion and sets the background color corresponding to the color of the ANTICO VELLUTO decorative coating.



superior of the orest of the or

L +7 (499) 685-45-47

pratta.xyz

☑ info@pratta.xyz

+7 (499) 685-16-25





 $pratta.xyz \cdot or sochem.com \cdot pratta.xyz \cdot o$

Application

The application of the ANTICO VELLUTO material should be applied with a special stainless steel spatula with rounded corners and a pointed base of the work surface. It is difficult to achieve the desired effect using another means.

The ANTICO VELLUTO material is applied in 2 stages (depends on the selected effect). Apply 1 layer of exclusive ANTICO VELLUTO material, covering the entire surface and leaving no gaps. The application technique is classical (Venetian). Drying time of the first layer: 4–6 hours.

Creating the effect of classic wet silk:

Apply a second layer of ANTICO VELLUTO material 2–3 times thicker than the previous one. It should be applied with a classical (Venetian) technique, tightly covering the surface and immediately forming a chaotic or directional texture of velvet. Drying time of the second layer: 6–8 hours.

Creating the effect of Florentine silk:

This effect is formed only on the second layer. Apply a second layer of ANTICO VELLUTO material 2–3 times thicker than the previous one, tightly covering the entire surface. Immediately after application, treat the surface with the same trowel with a clean work blade. The processing method should be performed with the smooth side of the trowel, completely leaning against the plane and with chaotic movements repeating the «eight» or «infinity sign». This is how the texture of Florentine silk is formed. The duration of texture formation determines the size and frequency of the silk pattern.



The ANTICO VELLUTO decorative coating lends itself perfectly to local restoration.

Drying time to workload: 24 days.

Technical characteristics

Application temperature: $+5 \div +35^{\circ}\text{C}$ Relative humidity: < 85% Drying by touch: 30 minutes Interlayer drying: 4-8 h Complete drying: 24 h

Specific gravity: 1,05–1,1 kg/Lt

pH: 7-8
Theoretical consumption: 6-8 m2

Color: basic standard, tinted Packaging: 0.75 lt, 4 lt, 15 lt



superior of the orest of the or

+7 (499) 685-45-47

pratta.xyz

☑ info@pratta.xyz

+7 (499) 685-16-25





 $pratta.xyz \cdot or sochem.com \cdot pratta.xyz \cdot o$

Technical characteristics

Application temperature: +10÷ +35°C
Relative humidity: <85%

Drying by touch: 2-4 h

Interlayer drying: 8-12 h

Complete drying: 24 h

Maximum strength set: 20–25 days

Maximum strength set: 20–25 days
Thickness (layer thickness): 0.5–1.0 mkm
Specific gravity: 1.6–1.7 kg/l
pH: 12-14
Theoretical consumption: 1÷0.7 m²/kg
Color: white, tinted

Appearance: matte, semi-gloss Packing: 6 kg, 24 kg

Tinting



Tinting is possible in a wide range of colors, including support for RAL and NCS systems. We recommend tinting with the help of pigments and the PCS (PRATTA COLOR SYSTEM) tinting system according to the catalogs of own colors for silk coatings of the «SETA» series. Care should be taken when using different batches of the same color material. Mix them together to ensure uniformity of color during application.

Storage





Product without tinting in packaged form, placed in a cool, dry place, has a shelf life of up to 24 months. After use, the packaging should be carefully closed and stored in an inverted position. Storage and transportation temperature: from $+5^{\circ}$ C to $+30^{\circ}$ C.

